

BAWATHANE 888

- Bawathane 888 is a class 180 Polyurethane wire enamel.
- Bawathane 888 possesses a high cut through & good solder ability
- Bawathane 888 has a good resistance to styrenated impregnation Resins

Physical Properties			
Appearance	Clear Liquid		
Solid Content 1g/180°C/1h	30 ± 1%	35 ± 1%	40 ± 1%
Size mm	0.05 to 0.500	0.5 to 2.0	1.6 to 5.0
* Viscosity	20 - 30	40-50	80-100
** Viscosity	60 - 100	130 - 170	250 - 350
Proposed Machine	horizontal machine for felt	horizontal & vertical plant for die	vertical plant for die
Flash Point	40°C		
Compatibility with thinner	1:1		

^{*} Viscosity by Din Cup 4 at 25° C in sec.

^{**} Viscosity by Viscometer at 23°C

Thermal Properties	
Heat Shock 2d/180°C/ 30min	ок
Cut Through 260°C / 2min	ок

Electrical Properties		
Break Down Voltage kV	at RT	9.5 kv

Please note that all above-mentioned values may be changed according to the machine.

Mechanical	Properties
Diameter of bare wire	1.0 mm
Build up of enamel	0.070 mm
Elongation	36%
Flexibility Mandrel Winding (15% prestretch 1xd)	ок
Jerk Test	ок
Peel Test (nxd)	N.A.
Abrasion (Av) (Unidirectional)	14N

Chemical P	roperties
Solderability at 375° C	>2 Sec
Pencil Hardness	
Initial	3h
Std. Solvent	2h
Solvent Resistance	,

Tan Delta	
Bending Point ^o C (solid block)	175-185

RECOMMENDED THINNER		Thinner W/E	
PACKING:	BAWATHANE 888 Thinner PW/E	200 Kg in mild steel drums. 21 Kg in mild steel drums.	
SHELF LIFE	One year from date of manufacturing if stored in sealed container (at room temperature 25°C).		

This information contained here is best to our knowledge. Company makes no warranty of results and assurance, no obligations or liabilities for the use of any products and process herein. This publication is not to be taken as a license to operate under or recommendation to infringe upon any patents.

HARMAN BAWA (P) LTD.

65, West Avenue Road, Punjabi Bagh West, New Delhi – 110 026 Ph: 011-25222629,25222083 (FAX.) 011-25227237