

BAWATHERM 2002

■ BAWATHERM 2002 is a Class 220 Polyamide-imide based wire enamel, wires coated with BAWATHERM 2002 is used as sole coat/overcoat to manufacture wires of Class 220 Bawatherm 2002 has excellent adhesion on wire upto 5.00mm.

Physical Properties			
Appearance	Clear Liquid		
Solid Content 1g/180ºC/1h	24 ± 1%	30 ± 1%	33 ± 1%
Size mm	0.05 to 0.80	0.50 to 1.80	1.00 to 5.00
* Viscosity	40 -50	70-100	100-120
** Viscosity	250 - 400	400 - 500	500 -750
Proposed Machine	horizontal machine for felt	horizontal & vertical plant for die	vertical plant for die
Flash Point	40°C		
Compatibility with thinner	1:1		

* Viscosity	, hv	Din	Cun	4	at '	25°	C	in	sec
" VISCOSIT\	/ DV	חוט	Cup	4	at .	Zo°	U	ın	sec.

^{**} Viscosity by Viscometer at 23°C

Thermal Properties			
Heat Shock 1dx240°C/ 30min	ок		
Cut Through 360°C/ 2min	ОК		

Electrical Properties				
Break Down Voltage kV	at RT	11.00 kv		

Please note that all above-mentioned values may be changed according to the machine.

Mechanical Properties			
Diameter of bare wire	1.0 mm		
Build up of enamel	0.070 mm		
Elongation	36%		
Flexibility Mandrel Winding (15% pre- stretch 1xd)	ок		
Jerk Test	ок		
Peel Test (nxd)	220		
Abrasion (Av) (Unidirectional)	13N		

Chemical Properties		
Solvent Resistance		
Pencil Hardness		
Initial	4h	
Std. Solvent	5h	

Tan Delta			
Bending Point °C (solid block)	220-250		

RECOMMENDED THINNER		Thinner W/E	
PACKING:	BAWATHERM 2002 Thinner PW/E	200 Kg in mild steel drums. 21 Kg in mild steel drums.	
SHELF LIFE	One year from date of manufacturing if stored in sealed container (at room temperature 25°C).		

This information contained here is best to our knowledge. Company makes no warranty of results and assurance, no obligations or liabilities for the use of any products and process herein. This publication is not to be taken as a license to operate under or recommendation to infringe upon any patents.

HARMAN BAWA (P) LTD.

65, West Avenue Road, Punjabi Bagh West, New Delhi – 110 026 Ph: 011-25222629,25222083 (FAX.) 011-25227237